




# Weicon VA 8312 Super Glue Info Sheet



**Cyanoacrylate Adhesives**

A one-part, cold curing adhesive with a very fast cure time and is designed for the bonding of numerous rubber materials (it is especially suitable for bonding EPDM) and plastics.

Utilised in combination with Weicon Contact Filler for the instant bonding and filling of cracks, gaps, holes and irregularities.



VA 8312 Cyanoacrylate has a low viscosity and is ISEGA Certified for use in the food and beverage sectors. This glue is a viable option for many hard to bond plastics when used in conjunction with our CA Primer.



**Cleaners & Degreasers**

General Surface Compatibility			
Metal	Compatible	Plastic*	Highly Compatible
Rubber	Highly Compatible	EPDM	Compatible
Wood	Not Suggested	Balsa Wood	Compatible
Glass / Ceramic	Not Suggested	Leather	Compatible


\*Low Surface Energy Types (e.g. PTFE, Polypropylene, Polyethylene only with special pre-treatment).



**Epoxy Adhesives**

Standard Sizes			
12gm	30gm	60gm	500gm

Key Specifications	
Max. Gap Coverage	0.1mm
Viscosity	20-40 mPa·s
Temp. Resistance Continuous	-50°C to +80°C
Initial Adhesion	
To Aluminium	30 - 60 Seconds
To NBR Rubber	2 - 10 Seconds
Shear Strength	
Sand-Blasted Steel	20 N/mm <sup>2</sup>
Rigid PVC	13 N/mm <sup>2</sup>
ABS	12 N/mm <sup>2</sup>
NBR	>8 N/mm <sup>2</sup>



**Primers & Accessories**

AG Sydney  
Head Office  
02 9774 3333

[syd@agaus.com.au](mailto:syd@agaus.com.au)

AG Queensland

07 3257 1144

[bris@agaus.com.au](mailto:bris@agaus.com.au)

AG Victoria

03 9768 3113

[melb@agaus.com.au](mailto:melb@agaus.com.au)

AG Western Australia

08 9258 5858

[perth@agaus.com.au](mailto:perth@agaus.com.au)

AG Newcastle

02 4967 7677

[new@agaus.com.au](mailto:new@agaus.com.au)

AG Wollongong

02 4272 4800

[woll@agaus.com.au](mailto:woll@agaus.com.au)

Visit [agaus.com.au](http://agaus.com.au) for more information and full contact details.