



## TECHNICAL SPRAYS



# Weicon Allround Lubricant AL-H

Weicon Allround Lubricants are high performance greases that provide very long lasting lubrication of highly stressed parts. These precision greases have been specially formulated to provide sustained protection against friction and wear and thus extending machinery service life.

Weicon Allround Lubricant AL-H has been specially formulated for use in the food industry. This grade withstands prolonged exposure to elevated temperatures and has been certified in accordance with NSF H1. It is typically used for the lubrication of rolling or sliding bearings, joints, spindles, spline shafts and linear guidance systems at all speeds that allow for grease lubrication.

### Technical Properties

Abbreviation (DIN 51502)	KPHC 1P -40
Consistency Assignment (DIN 51818)	NLGI-Class 1
Basis	Aluminium Complex Soap Polyalphaolefine
Colour	Yellowish-White
VKA-Test (DIN 51350) Welding Load	1,800 N
VKA-Test (DIN 51350) Goods Load	1,700 N
VKA-Test (DIN 51350) Spherical Cap Value (1 Min / 1000)	0.6mm
Speed Identifying Value	400 000
Worked Penetration (DIN ISO 2137)	310-340 1/10mm
Water Resistance (DIN 51807)	1 – 90
Temperature Resistance	-40°C to +160°C
Drop Point (IP 396)	>200°C
Kinematic Viscosity (DIN 51562) +40°C	400mm <sup>2</sup> /s (approx.)
Kinematic Viscosity (DIN 51562) +100°C	40mm <sup>2</sup> /s (approx.)
EMCOR-Corrosion Test (DIN 51802)	1 / 1
Density at +20°C (DIN 51757)	0.93 g/cm <sup>3</sup>
Conforms to	NSF-H1, LMBG Section 31 and Section 21

### Application Selection Table

	AL-H		AL-H		AL-H
Rolling Bearings	•	Sliding Guides	•	Camshafts	
Sliding Bearings	•	Linear Guide Systems	•	Springs	
Chains		Spindles	•	Open Gears	
Joints	•	Spline Shafts		Worm Gears	
Levers	•			Cables	

Visit: [www.agaus.com.au](http://www.agaus.com.au)

Phone: 1300 098 060

#### Important

This information should not be treated as a substitute for specific technical advice. AG does not offer such advice and cannot warrant the performance or suitability of products for particular applications.

## Weicon Allround Lubricant AL-H

### Type of lubricating grease:

K, G, OG, M

- Information with respect to the operative range (in the case of synthetic oil additional letter based on type of oil: HC,E,PG,S)

Additional identifying letter: D,E,F,L,M,S,PV

- Information with respect to the usability

Consistency class (NLGI)

Lower temperature operative range

**KF 2 K-20**

Additional identifying letter C to U

- Statement of the upper temperature operative range

1	2	3
Lubricating grease	Identifying letter	Symbol
Lubricating greases for rolling and sliding bearings and sliding surfaces in accordance with DIN 51825	K <sup>1)</sup>	For lubricating greases based on mineral oil 
Lubricating greases for closed gears in accordance with DIN 51826	G	
Lubricating greases for open gears, gearing (adhesive lubricants without bitumen)	OG	
Lubricating greases for sliding bearings and seals <sup>2)</sup>	M	
Lubricating greases with a synthetic base are classified like the aforementioned greases based on mineral oil in terms of the basic properties.	Addition to the identifying letters in accordance with Table 1, Material group 3	For lubricating greases with a synthetic oil base 

<sup>1)</sup> ISO/TR 3498: 1986 uses the letters XM for the identifying letter K  
<sup>2)</sup> Lower demands than those placed on K lubricating greases

1	2
Consistency identifying number (NLGI classes in accordance with DIN 51818)	Worked penetration determined based on DIN ISO 2137 units <sup>1)</sup>
000	445 to 475
00	400 to 430
0	355 to 385
1	310 to 340
2	265 to 295
3	220 to 250
4	175 to 205
5	130 to 160
6	85 to 115 <sup>2)</sup>

<sup>1)</sup> 1 unit = 0.1mm / <sup>2)</sup> Stationary penetration

1	2
Additional identifying number	lower application temperature
-10	-10°C
-20	-20°C
-30	-30°C
-40	-40°C
-50	-50°C
-60	-60°C

### Additional identifying letters for synthetic oils

E	organic ester
FK	perfluor liquids
HC	synthetic hydrocarbons
PH	esters of phosphoric acid
PG	polyglycol oils
SI	silicon oils
X	others

1	2
Additional identifying letter	Lubricants
D	For lubricating oils with detergent additives, e.g. hydraulic oil HLPD
E	For lubricating oils, which are used mixed with water, e.g. water mixable cooling lubricants, e.g. SE cooling lubricant
F	For lubricating oils, which are used mixed with water, e.g. water mixable cooling lubricants, e.g. SE cooling lubricant
L	For lubricant oils with active substances to increase the protection against corrosion and/or the aging stability, e.g. lubricant oil DIN 51517 - CL 100
M	For water mixable cooling lubricants with mineral oil contents, e.g. SEM cooling lubricant
S	For water mixable cooling lubricants with a synthetic base, e.g. SES cooling lubricant
P	For lubricants with active substances to reduce the friction and wear in the mixed friction area and/or to increase the stability under load, e.g. CLP 100 lubricating oil
V <sup>1)</sup>	For lubricants, which are diluted with solvents, e.g. DIN 51513-BB-V lubricating oil

<sup>1)</sup> The additional identifying letter V sometimes necessitates labelling in accordance with the Hazardous Substances Act (GefStoffV).

1	2	3
Additional identifying letter	upper application temperature <sup>1)</sup>	Behaviour with water in accordance with DIN 51807 Part 1 Evaluation scale DIN 51807 - <sup>2)</sup>
C	+60°C	0-40 or 1-40
D		2-40 or 3-40
E		0-40 or 1-40
F	+80°C	2-40 or 3-40
G		0-90 or 1-90
H	+100°C	2-90 or 3-90
K		0-90 or 1-90
M	+120°C	2-90 or 3-90
N		by arrangement
P	+140°C	
R	+160°C	
S	+180°C	
T	+200°C	
U	+220°C	
	more than +220°C	

<sup>1)</sup> The „upper application temperature“ for permanent lubrication is equal to the highest test temperature when testing in accordance with DIN 51806 part 2 (e.g. draft) and/or DIN 51821 part 2, if the test runs are passed.  
<sup>2)</sup> 0 means no change  
 1 means slight change  
 2 means moderate change  
 3 means considerable change

Visit: [www.agaus.com.au](http://www.agaus.com.au)

Phone: 1300 098 060

### Important

This information should not be treated as a substitute for specific technical advice. AG does not offer such advice and cannot warrant the performance or suitability of products for particular applications.



# Weicon Allround Lubricant AL-H

## Miscibility with other Greases

Optimum results with Weicon Allround Lubricant high performance greases will only be achieved through the complete removal of grease residues. However, in practice, such thorough removal is not always possible. In these cases you must first check whether the grade of Allround Lubricant you plan on using is compatible with the grease residues that will remain in the application area. This test must be carried out on the basis of the main components of the grease (basic oil and thickener). Both main components must be miscible (compatible).

### Miscibility of Basic Oils

Basic Oil	AL-H (Polyalphaolefine)
Mineral Oil	++
Ester	++
Polyglycol	-
Silicone (Metyl)	-
Silicone (Phenyl)	-
Polyphenylether	-
Perfluoropolyether Oil	-

### Miscibility of Thickeners

Thickening Agent	AL-H (Al Complex Soap)
Ca Soap (Water-Free)	-
Ca Complex Soap	-
Li Complex Soap	++
Li/Ca Soap	-
Li Soap	-
Na Soap	-
Gels	-
Ba Complex Soap	++
Polycabamide	++

### Compatibility with other Sealing Materials and Polymers

ABS – ABS Copolymeride	++	PE – Polyethylene	++
ACM – Acrylate Rubber	++	PET – Polyethyleneterephthalate	++
CA – Cellulose Acetate	++	POM – Polyoxymethylene	++
CR – Chloroprene Rubber	+	PP – Polypropylene	++
CSM – Chlorosulfonated PE Rubber	++	PPO – Polyphenylene Oxide	++
EPDM – Ethylene Propylene Diene Rubber	-	PS – Polystyrene	++
EPS – Expanded Polystyrene	++	PTFE – Polytetrafluoroethylene	++
FKM – Fluorocautchoc	++	PUR – Polyurethane	++
LDPE – Low Density Polyethylene	++	PVC – Polyvinylchloride	++
NBR – Nitrile Butadiene Rubber	++	SBR – Styrene Butadiene Rubber	-
NR – Natural Rubber	-	SQM/MVQ – Silicone Rubber	-
PA – Polyamide	++	TPE – Thermoplastic Elastomers	-
PC – Polycarbonate	+	UHMWPE – Ultra High Molecular Weight Polyethylene	++

++ Resistant

+ Resistant to a limited extent

- Not Resistant

## Storage

Keep in closed original container. Do not store with oxidising agents. Keep container tightly closed and store in a cool and well aired place. Minimum shelf life for Weicon Allround Lubricants is 24 months.

## Availability

Weicon Allround Lubricant AL-H is available in the following sizes and forms.

- 400gm Cartridges
- 1kg Containers
- 5kg Buckets
- 25kg Buckets

Visit: [www.agaus.com.au](http://www.agaus.com.au)

Phone: 1300 098 060

### Important

This information should not be treated as a substitute for specific technical advice. AG does not offer such advice and cannot warrant the performance or suitability of products for particular applications.