

Anti-Seize Nickel Assembly Paste



| | |
|------------------------------|-----------------------|
| Sulfur content (DIN 514) | <0,1 % |
| Water resistance (DIN 51807) | 1 - 90 |
| Pressure (DIN 53281-83) | 230 N/mm ² |
| Salt spray test | > 170 h |
| Temperature resistance | -30 to 1.450 °C |

Assembly Paste for extreme conditions

The assembly paste was developed to resist extreme conditions. It is highly sticky, water repellent and resistant to sweet, salt and hot water as well as steam. The high nickel component furthermore provides protection against corroding and corrosive solvents which are contained in diluted hydrochloric acid, sulphur or nitric acid, among others. Anti-Seize Nickel can be applied at a large temperature range between -30°C to +1,450°C.

Anti-Seize Nickel serves as corrosion protection and high-performance fitting grease for static and dynamically extremely stressed screw connections and installation parts and the application at slowly rotating system in the high-temperature range.

The paste protects against corrosion, seizing, wear, stick-slip effects, oxidation and friction corrosion as well as electrolytic reactions, the so-called cold-sealing. For example, Anti-Seize Nickel can be used on seals, valves, screw connections, gear wheels, bearings, jets, conveyor belts, studs, tools or cylinders.

Technical Data

| | |
|---|--------------------------|
| Basic Oil | Synthetic oil |
| Colour | anthracite |
| Density at +20°C (+68°F) (DIN 51757) | 1,3 g/cm ³ |
| OFW device coefficient of friction | 0,16 |
| Friction total | 0,15 µ |
| Friction thread | 0,14 µ |
| Friction head bottom | 0,16 µ |
| VKA-TEST (DIN 51350) welding load | 0,6 N |
| VKA-TEST (DIN 51350) Spherical cap value (1Min/1000N) | 2.000 mm |
| Worked penetration (DIN ISO 2137) | 310 - 340 1/10 mm |
| Specific heat transfer capacity (20°C) | 1,493 J/(g·K) |
| Thermal diffusivity (20°C) | 0,303 mm ² /s |
| Thermal conductivity (ISO 22007-4) (20°C) | 0,582 W/m·K |
| Dielectric strength (DIN EN 60243-1) (20°C) | 1,1 kV/mm |

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

Surface pre-treatment

Clean and degrease surfaces. Apply the assembly paste evenly. AS is suitable only for assembly paste specific applications, it does not replace pure lubricants and greases.

Processing

Apply a good quantity of Assembly Paste with a brush, cloth or plastic sponge. On threads it is important that Assembly Paste is applied down to the thread root to ensure a good sealing effect. Assembly Paste must not be mixed with greases or oils to avoid changes in the material characteristics. WEICON Assembly Pastes do not replace oil or grease lubrication.

Storage

Keep container tightly closed. Do not store together with oxidizing agents. Store in a dry place at storage temperature. Original container are storable for 24 months.

Safety and health

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Available sizes:

| | |
|----------|---|
| 26050012 | Anti-Seize Nickel Assembly Paste 120 g |
| 26050040 | Anti-Seize Nickel Assembly Paste 400 g |
| 26050045 | Anti-Seize Nickel Assembly Paste 450 g |
| 26050050 | Anti-Seize Nickel Assembly Paste 500 g |
| 26050100 | Anti-Seize Nickel Assembly Paste 1 kg |
| 26050180 | Anti-Seize Nickel Assembly Paste 1,8 kg |
| 26050500 | Anti-Seize Nickel Assembly Paste 5 kg |
| 26050910 | Anti-Seize Nickel Assembly Paste 10 kg |
| 26050920 | Anti-Seize Nickel Assembly Paste 20 kg |

Accessories:

| | |
|----------|---------------------------|
| 10953001 | Processing Spatula, short |
| 10953003 | Processing Spatula, long |

WEICON GmbH & Co. KG
(Headquarters)
Germany
phone +49 (0) 251 9322 0
info@weicon.de

WEICON Middle East L.L.C.
United Arab Emirates
phone +971 4 880 25 05
info@weicon.ae

WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca
www.weicon.ca

WEICON Kimya Sanayi Tic. Ltd. Şti.
Turkey
phone +90 (0) 212 465 33 65
info@weicon.com.tr
www.weicon.com.tr

WEICON Romania SRL
Romania
phone +40 (0) 3 65 730 763
office@weicon.com
www.weicon.com.ro

WEICON SA (Pty) Ltd
South Africa
phone +27 (0) 21 709 0088
info@weicon.co.za

WEICON South East Asia Pte Ltd
Singapore
phone (+65) 6710 7671
info@weicon.com.sg

WEICON Czech Republic s.r.o.
Czech Republic
phone +42 (0) 417 533 013
info@weicon.cz
www.weicon.cz

WEICON Ibérica S.L.
Spain
phone +34 (0) 914 7997 34
info@weicon.es
www.weicon.es

WEICON Italia S.r.l.
Italy
phone (+39) 0102924871
info@weicon.it
www.weicon.it