



Weicon Speed-Flex

Weicon Speed-Flex is a high quality, MS Polymer based adhesive designed to replace traditional fixing and fastening methods. This grade creates high strength bonds and has a pasty viscosity for very accurate application. Speed-Flex bonds well to a range of materials, is resistant to ageing, weathering and UV and is free of silicone, isocyanate and halogen. It is ISEGA recognised as an adhesive for foodstuff technology.

Features

- Creates high strength bonds
- Adheres to a wide range of materials
- Resistant to weathering and UV
- Free of silicone, isocyanate and halogen
- Solvent-free, odour-free, non-corrosive
- Can be painted over immediately (wet in wet)
- Sandable after complete curing
- ISEGA recognised for use in foodstuff technology

Applications

- Tank construction
- Drywall repair and construction
- Shop fittings and interior wall
- Metalworking
- Tank and apparatus construction
- Ventilation and air conditioning
- All areas where sealants/adhesives that contain silicone are not permitted

Properties

Basis	One Component MS Polymer
Density	1.6 g/cm ³
Viscosity	Extremely Pasty
Stability/Run-Off ASTM D 2202	<1mm
Processing Temperature	+5°C to 35°C
Curing Conditions	+5°C to 40°C and 30% to 95% Relative Humidity
Skin-Over Time	10 min.
Cure Speed (first 24 Hours)	2-3mm
Volume Change (DIN 52451)	-1%
Gap Filling up to Max.	5mm
Gap Width up to Max.	5mm
Shelf Life (+5°C to 25°C)	12 Months
Shore Hardness A (DIN 53505 / ASTM D 2240) ± 5	58
Elongation at Break (DIN 53504 / ASTM D 412)	230%
Tensile Strength of the Pure Adhesive/Sealant	2.2 N/mm ²
Average Tensile Shear Strength (DIN 53283)	1.3 N/mm ²
Tear Strength (DIN 53515 / ASTM D 624)	10 N/mm ²
Movement Capacity Max.	15%
Temperature Resistance	-40°C to +80°C (Continuous) Up to 120°C for up to 2 hours.
Overpaintable (liquid paint)	Only using "wet in wet" within 3 hours (max.) after material application.
Building Material Category (DIN 4102)	B 2

Visit: www.agaus.com.au

Phone: 1300 098 060

Important

This information should not be treated as a substitute for specific technical advice. AG does not offer such advice and cannot warrant the performance or suitability of products for particular applications.



Weicon Speed-Flex

Speed-Flex Chemical Resistance After Curing

2-Propanol	-	Hydrogen Peroxide (3%)	+
Acetic Acid (<5%)	+	Ketones	-
Acetone	-	Lyes (diluted)	+
Alcohol	O	Methanol	-
Ammonia (10%)	+	Methyl Ethyl Ketone	-
Antifreeze	+	Motor Oil (Mineral and Synthetic)	-
Caustic potash solution (20%)	O	+140°C	-
Citric Acid (10%)	-	Motor Oil (Mineral and Synthetic)	-
Concentrated Formic Acid	-	Naphtha	-
Concentrated Phosphoric Acid	-	Nitric Acid (5%)	-
Concentrated Silicon Oil	+	Paint Thinner	-
Cooling Lubricant (Water Dilutable)	+	Paraffin Oil	-
Diesel / Heating oil	-	Petrol (92 to 100 octane)	-
Edible Oil / Vegetable Oil	O	Phosphoric Acid (5%)	-
Ethanol	-	Salt Water / Sea Water	+
Freon	-	Sodium Hydroxide Solution (20%)	-
Gear Oil	-	Sulphuric Acid (5%)	-
Glycerine (glycol)	+	Toluene	-
Glycol Ether	-	Water	+
Hydraulic Oil	O	Water (90°C)	+
Hydrochloric Acid (5%)	-	Xylene	-

+ = Resistant

O = Resistant for a Limited Time

- = Not Resistant

Preparation of the Surface

The surface to which Speed-Flex will be applied must be clean and grease-free. Many surface contaminants (e.g. oil, dust and dirt) can be removed with Weicon Surface Cleaner. For heavily soiled surfaces we suggest Weicon Cleaner S Spray. Weicon Sealant and Adhesive Remover is suitable for removing old paint or adhesive residues.

Most materials can be bonded well to themselves and among each other. For certain materials or extreme requirements, we suggest the use of an adhesion agent or primer. More information on these are available from Associated Gaskets. Alternatively, a mechanical surface pre-treatment (e.g. sanding or sand-blasting) can considerably improve adhesion.

Visit: www.agaus.com.au

Phone: 1300 098 060

Important

This information should not be treated as a substitute for specific technical advice. AG does not offer such advice and cannot warrant the performance or suitability of products for particular applications.



ADHESIVES & SEALANTS



Weicon Speed-Flex

Processing

Solar-Flex is supplied in cartridge form and should be applied using a professional quality cartridge gun (such as our Weicon Cartridge Gun "Special").

Joining the parts being bonded

To ensure optimum wetting, the parts must be joined before the first skin has formed on the adhesive (skin-over time).

Curing

All Weicon elastic one part adhesives and sealants cure by reacting with humidity in the surrounding environment. The curing process starts at the surface of the adhesive and proceeds inwards from there. At 50% relative humidity and 23°C, the cure speed is approximately 3mm in the first 24 hours.

Adhesive bonds of large surfaces and high layer thicknesses cure more slowly as the humidity cannot penetrate as quickly towards the inside of the adhesive if the outer layers have already cured. Higher temperature and/or higher humidity accelerates curing while lower temperatures and/or lower humidity slows it down.

Storage

When stored unopened and in normal climatic conditions (23°C and 50% relative humidity) Weicon Speed-Flex has a minimum shelf-life of 12 months.

Availability

Weicon Speed-Flex is available in white (RAL Colour Code 9003) or grey (RAL 7000). Both colours are supplied in 310ml cartridges.

Visit: www.agaus.com.au

Phone: 1300 098 060

Important

This information should not be treated as a substitute for specific technical advice. AG does not offer such advice and cannot warrant the performance or suitability of products for particular applications.